

BZ-4300 Non-Silicone Defoamer

Composition: vinyl polymer

Appearance: colorless to light yellow transparent liquid

Active portion: 100%

Application range: solvent coating; light curing coating, solvent-free coating.

Recommended dosage: Total formula 0.1-0.5% (test the most appropriate dosage before use)

Usage: In order to obtain sufficient defoaming effect, it is recommended to add before grinding. If added later, it should be mixed under a sufficiently high shear force to ensure the defoaming effect.

Features and advantages:

1. It has high efficiency of defoaming and foam suppression, is versatile, does not contain solvent, and is suitable for low VOC system.
2. It has long-term stability and can maintain defoaming performance for a long time without affecting the recoating and adhesion, and will not produce shrinkage holes.
3. Suitable for polyester, unsaturated polyester, epoxy and light curing system;

Package: 25KG/180kg non-recyclable blue barrel.

The lid must be tightly closed after use if the product is not completely used.

Storage: keep away from heat source, light source and avoid light.

Precautions: Carefully evaluate the effects on solubility and crater before use.

The above information is based on the product situation. Due to different producer formula, production process and construction conditions, the above statement is for reference only. The company does not assume any legal responsibility, please test the dosage before use. The company reserves the right to improve its products and any changes in specifications will not be notified in advance.