

## BZ-066A Special Organic Silicon Defoamer

**Composition:** polyether modified siloxane

**Appearance:** colorless to yellowish transparent liquid

**Non-volatile matter:** 2.0%

**Solvent:** D80 solvent

**Application range:** solvent based coating, light curing coating, solvent free coating.

**Recommended dosage:** Total formula 0.05-0.5% (test the most appropriate dosage before use)

**Usage:** To achieve sufficient defoaming effect, it is recommended to add before grinding. If added later, mix under sufficiently high shear force to ensure the good distribution of defoamer.

### Features and advantages:

1. It has high efficiency of defoaming and foam suppression, and has a very high defoaming effect on the micro bubbles in the coating products.
2. Especially suitable for white paint and color paint with good defoaming effect.
3. It has a good effect on eliminating the bubble of UV coating machine and does not contain benzene solvents.

**Package:** 25KG/180kg non-recyclable blue barrel.

The lid must be tightly closed after use if the product is not completely used.

**Storage:** keep away from heat source, light source and avoid light.

**Precautions:** Carefully evaluate the effects on solubility and crater before use.

The above information is based on the product situation. Due to different producer formula, production process and construction conditions, the above statement is for reference only. The company does not assume any legal responsibility, please test the dosage before use. The company reserves the right to improve its products and any changes in specifications will not be notified in advance.