

## BZ-66 Silane Modified Defoamer

**Composition:** Organic silicon oxygen polymer

**Appearance:** milky white liquid

**Active portion:** 100%

**Application range:** solvent based coating; light curing coating, solvent free coating.

**Recommended dosage:** Total formula 0.1-1.0% (test the most appropriate dosage before use)

**Usage:** In order to obtain sufficient defoaming effect, it is recommended to add before grinding. If added later, mix under a sufficiently high shear force to ensure good distribution of the defoamer.

### Features and advantages:

1. It has a strong ability to break and suppress bubbles, can quickly eliminate foam in various systems, and has a fast defoaming speed and long time of suppressing bubbles. It has a good effect at low dosage.
2. It has a good effect of defoaming and suppressing foam in the manufacturing and construction process of high solid content and solvent-free epoxy coatings, especially for high viscosity, high film thickness and solvent-free high film thickness epoxy floor coatings and ink systems.

**Package:** 25KG non-recyclable blue barrel.

The lid must be tightly closed after use if the product is not completely used.

**Storage:** keep away from heat source, light source and avoid light.

**Precautions:** Carefully evaluate the effect on solubility and crater before use.

The above information is based on the product situation. Due to different producer formula, production process and construction conditions, the above statement is for reference only. The company does not assume any legal responsibility, please test the dosage before use. The company reserves the right to improve its products and any changes in specifications will not be notified in advance.