

101# 102# Dibutyltin dilaurate

Composition: Divalent organotin compounds

Appearance: Yellowish transparent liquid

Tin content: 101#:18%; 102#:10.5%

Recommended dosage: Total formula amount amount 0.1-0.8%

Usage: used as catalyst and foaming activator for polyurethane foam plastic, PVC foam plastic and silicone rubber synthetic material.

Features and advantages:

1. This kind of organic tin is a basic hardener, easy to dissolve in organic solvents, with good oxidation stability, and can be used as a catalyst in double polyurethane, polyester, nitro paint, electroplating coating, adhesive, sealant, ink and other coatings and moisture curing coatings.
2. Used as a heat stabilizer for silicone rubber mold products and soft PVC plastic products, such as film, semi-rigid sheet, transparent hose, etc.

Package: 25KG non-recyclable blue barrel.

The lid must be tightly closed after use if the product is not completely used.

Storage: keep away from heat source, light source and avoid light.

Precautions: Carefully evaluate the specific amount in the system before use.

The above information is based on the product situation. Due to different producer formula, production process and construction conditions, the above statement is for reference only. The company does not assume any legal responsibility, please test the dosage before use. The company reserves the right to improve its products and any changes in specifications will not be notified in advance.