



JM-4103 热塑性丙烯酸树脂 (技术数据表)

【特 性 Features】

- 铝粉定向, 附着力优异, 耐水;
Aluminum powder orientation, excellent adhesion, water resistance;
- 与 CAB 相容性好;
Good compatibility with CAB;
- 快干性, 施工性;
Fast drying and construction performance;
- 颜料润湿性, 无苯;
Wettability of pigments, benzene free;

【用 途 Application】

- 工业用途的银粉漆和色漆
Silver powder paint and colored paint for industrial use
- 汽车修补漆
Automotive repair paint
- 塑胶漆
Plastic paint

【性 质 Properties】

组成部分	丙烯酸树脂
Component	Acrylic resin
外观	透明粘稠液体
Appearance	clear, sticky liquid
不挥发份	50±2%
Non volatiles	
溶剂	TOL/I-BUOH
Solvent	
色度	≤1# (Fe-Co)
Color	
粘度	200~300s/ 25°C (涂-4 杯)
Viscosity	
酸价	3~5 mgKOH/g
Acid value	

【溶解性 Dilutability】

可用芳烃类、酯类、酮类和醚酯类等溶剂稀释, 在脂肪烃溶剂中溶解度有限。

Can be diluted with solvents such as aromatic hydrocarbons, esters, ketones, and ether esters, but has limited solubility in aliphatic solvents.

【参考配方 Reference Formula】

单组份色漆		稀释剂	
JM-4103 树脂	70	TOL	20
BZ-6310 流平剂	0.2	XYL	25
通用色浆	5	BAC	20
BAC	10	EA	10
TOL	6.8	IPA	10
XYL	8	BCS	15
100		100	

【包 装 Packing】

净重 Net weight 200KG/桶

【储 存 Storage】

产品用密封容器包装, 储存温度建议在 0~40°C 范围内, 储存于阴凉处, 避免日晒雨淋, 远离火源, 本产品自生产日起, 保质期限为 12 个月。在冬季温度低于 0°C 时应避免霜冻, 使用前请进行必要的检测。

The product is packaged in a sealed container. The storage temperature is recommended to be within the range of 0~40°C. It should be stored in a cool place, away from the sun and rain, and away from fire. The shelf life of this product is 12 months from the date of production. Frost should be avoided when the temperature is below 0°C in winter. Please conduct necessary tests before use.