TEL: 0757-26620881/0751-3836368

UEL: Http://www.camen.cn

JM-2270 Hydroxyl Acrylic Resin

(Technical Data Sheet)

[Property]

- Good compatibility and gloss
- Good leveling and appearance
- Good mechanical and chemical properties

[Uses]

- Industrial varnish and enamel
- Refinish Paint for Automotive, Railway and Other Transport Machinery

[Properties]

Constituent Acrylic Resin

Appearance Clear transparent liquid

Non-volatile matter 69~71%

Solvent Xylene

Specific Gravity Approximately 1.00 Kg/dm³

Colority < 100APHA

Viscosity 2500-6500

Acid Value 5.0~8.0mgKOH/g (Supply Value)

OH Value Approximately 100mgKOH/g (Solid)

OH% Approximately 3.0%(Solid)

[Solubility]

	Dilutable
Petroleum Ether	_
Xylene	+
Toluene	+
Ethyl Acetate	+
Butyl Acetate	+
Acetone	+
PGMEA	+
+ = Soluble in	
○ = Partially soluble	

○ = Partially soluble

- = Insoluble

[Storage]

The product is packed in sealed containers. It is recommended to store it at a temperature range of 0~40°C in a cool place, protected from sunlight and rain, and away from sources of ignition. The shelf life of this product is 12 months from the date of production. When the temperature drops below 0°C in winter, it should be protected from frost. Please conduct necessary tests before use.

[Packaging]

Net weight 200KG/Drum